



TEST REPORT

SHMR220700189601

Date: Jul 19, 2022

Page: 1 of 3



CUSTOMER NAME: NANJING FEELING RUBBER & PLASTIC PRODUCES CO.,LTD ADDRESS: NO.11 LANHUA ROAD, QIAOLIN INDUSTRIAL PARK, PUKOU

DISTRICT, NANJING, P.C:211100, CHINA

Sample Name : EPDM FLOOR

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

: SHIN2207016925CM-NJIN2206002783PS SGS Ref. No.

Date of Receipt Jul 05, 2022 Jul 05, 2022 **Testing Start Date**

Testing End Date : Jul 19, 2022

: For further details, please refer to the following page(s) Test result(s)

(Unless otherwise stated the results shown in this test report refer only

to the sample(s) tested)

Signed for Brasil. SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd.

And And Authorized signatory Constraint de la comuna de l







TEST REPORT

No.: SHMR220700189601

Date: Jul 19, 2022

Page: 2 of 3

Summary of Results:

No.	Test Item	Test Method	Result	Conclusion
1	Tensile Strength	BS 7188:1998+A2:2009	2.95 MPa	Pass
	Elongation at Break		601 %	

Note: Pass: Meet the requirements;

Fail: Does not meet the requirements;

/ : Not Apply to the judgment.

Original Sample Photo:









TEST REPORT

No.: SHMR220700189601

Date: Jul 19, 2022

Page: 3 of 3

Test Item: Tensile Test

Sample Description: Rubber part Test Method: BS 7188:1998+A2:2009

Test Condition:

Specimen thickness: 2.061 mm Testing speed: 100 mm/min Gauge length: 50 mm

Lab Environmental Condition: (23 ± 2) °C, (50 ± 5) % RH

Test Result:

		V	
		Requirement in BS	
Test Item	Test Result	7188:1998+A2:2009	Conclusion
	75	Section 8	
Tensile Strength	2.95 MPa	≥0.4 MPa	Pass
Tensile Strength Elongation at Break Ite: Test specimens were cu	601 %	≥75 %	Pass
e: Test specimens were cu	t from the sample.		Eill-
2	1	26	125
EL		101	B
		ay alle	
	****** End of repor		3.
	. 0	F. 0 P. 30	>
	ORK	anto Gi	
	CTO N	le. Fa	
	SUC STAIL	de	
	The low me		
an	Nic. Way		
CO.	40. Co.		
100	, -		
40%			
6.			

